

Scapa 9080B

30-Day UV Resistant Paper Masking Adhesive Tape - Indoor and Outdoor Use, 80°C

DESCRIPTION

Scapa 9080B is a 0.13mm semi crepe tape coated with an acrylic adhesive system resistant to ultraviolet rays for inside and outside usage. Scapa 9080B is a 30 days application and resists up to 80°C

APPLICATIONS

- Suitable for protecting a wide variety of surfaces such as steel, aluminium, wood or glass.
- Suitable for all general purpose 80°C indoor and outdoor bonding, holding, sealing and masking applications
- Suitable for both brush and spray air drying paints
- Masking tape for long term application (30 days), and U.V. resistant.
- Premium masking tape for building and painters masking applications; indoor and outdoor usage.

PRODUCT BENEFITS

- Temperature resistance: +80°C (60 minutes)
- Resistant to oven baking.
- Resistant to chemicals, lacquers and solvents.
- Conformable
- No staining.
- Good shear and holding strength.
- Good peel adhesion.
- Excellent paint flake resistance.
- Smooth and controlled unwind.
- UV RESISTANCE : easy removal after 30 days of exposure, no residual left
- Clean and easy removal.

TECHNICAL PROPERTIES

Technical Property	Nominal Value	Unit	Test Method
Adhesion to Steel	1.4	N/cm	AFERA 5001
Elongation at Break	11	%	AFERA 5004
Tensile Strength	29	N/cm	AFERA 5004
Total Thickness	135	µm	AFERA 5006

STANDARD PRESENTATIONS

- Colours: Blue
- Core: 76 mm Scapa branded cardboard core
- Packaging: Various packaging available
- Roll Length: 50m
- Roll Width: 25; 38; 50; 110 mm

RECOMMENDATIONS

The rolls should be stored flat on their cut edges in the original packaging. The product must be protected from dust, heat, moisture, direct sunlight and solvent fumes. Storage temperature between +10°C and +30°C. Under these conditions, the storage life of the tape in a temperate climate should not exceed 6 months. Surfaces should be clean, dry and free of dust, grease, oil or other contaminants.

Scapa masking tapes are not suitable for outdoor exposure and should not be submitted to prolonged periods of sunlight, as tapes may become difficult to remove. Clean removal may also vary with surface type, lacquers, primers and paints nature as well as the temperature of the surface at removal. For best results, remove the tape as soon as possible after applying the paints pulling it slowly at a 45° angle with constant speed. Because of the diversity of substrates used by the end user, the test conducted by the end user himself is the safest way to test the substrates before the final application